



# Bulk Asbestos Analysis

By Polarized Light Microscopy  
 EPA Method: 600/R-93/116 and  
 40 CFR, Part 763, Subpart E, App.E



**Customer:** JTL Services  
 3999 Sanderosa Rd.  
 Fayetteville, NC 28312

**Attn:** Jay Leonard

**Lab Order ID:** 10079435

**Analysis:** PLM

**Date Received:** 04/09/2025

**Date Reported:** 04/09/2025

**Project:** COF- 0418-96-1283 1661 Baysden Ct.  
 Fayetteville NC

Sample ID	Description	Asbestos	Fibrous Components	Non-Fibrous Components	Attributes
Lab Sample ID	Lab Notes				Treatment
1	Ceiling Surfacing	None Detected		100% Other	Off-white Non-Fibrous Homogeneous
10079435_0001					Crushed
2	Ceiling Surfacing	None Detected		100% Other	Off-white Non-Fibrous Homogeneous
10079435_0002					Crushed
3	Ceiling Surfacing	None Detected		100% Other	Off-white Non-Fibrous Homogeneous
10079435_0003					Crushed
4	Ceiling Surfacing	None Detected		100% Other	Off-white Non-Fibrous Homogeneous
10079435_0004					Crushed
5	Ceiling Surfacing	None Detected		100% Other	Off-white Non-Fibrous Homogeneous
10079435_0005					Crushed
6	Joint Compound	None Detected		100% Other	White Non-Fibrous Homogeneous
10079435_0006					Crushed
7	Joint Compound	None Detected		100% Other	White Non-Fibrous Homogeneous
10079435_0007					Crushed
8	Joint Compound	None Detected		100% Other	White Non-Fibrous Homogeneous
10079435_0008					Crushed

Disclaimer: Due to the nature of the EPA 600 method, asbestos may not be detected in samples containing low levels of asbestos. We strongly recommend that analysis of floor tiles, vermiculite, and/or heterogenous soil samples be conducted by TEM for confirmation of "None Detected" by PLM. This report relates only to the samples tested and may not be reproduced, except in full, without the written approval of SAI. This report may not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. government. Analytical uncertainty available upon request. Scientific Analytical Institute participates in the NVLAP Proficiency Testing program. Unless otherwise noted blank sample correction was not performed. Estimated MDL is 0.1%.

Lachlan Krenz (12)

Analyst

Approved Signatory



# Bulk Asbestos Analysis

By Polarized Light Microscopy  
EPA Method: 600/R-93/116 and  
40 CFR, Part 763, Subpart E, App.E



**Customer:** JTL Services  
3999 Sanderosa Rd.  
Fayetteville, NC 28312

**Attn:** Jay Leonard

**Lab Order ID:** 10079435

**Analysis:** PLM

**Date Received:** 04/09/2025

**Date Reported:** 04/09/2025

**Project:** COF- 0418-96-1283 1661 Baysden Ct.  
Fayetteville NC

Sample ID	Description	Asbestos	Fibrous Components	Non-Fibrous Components	Attributes
Lab Sample ID	Lab Notes				Treatment
9	Sheetrock	None Detected		100% Other	Off-white Non-Fibrous Homogeneous
10079435_0009					Crushed
10	Roofing Felt	None Detected	90% Cellulose	10% Other	Black, Brown Fibrous Homogeneous
10079435_0010					Teased, Dissolved
11	Roofing Shingles	None Detected	20% Fiber Glass	80% Other	Black Non-Fibrous Heterogeneous
10079435_0011					Dissolved, Crushed
12	Insulation	None Detected	98% Fiber Glass	2% Other	Brown Fibrous Homogeneous
10079435_0012					Teased, Crushed

Disclaimer: Due to the nature of the EPA 600 method, asbestos may not be detected in samples containing low levels of asbestos. We strongly recommend that analysis of floor tiles, vermiculite, and/or heterogenous soil samples be conducted by TEM for confirmation of "None Detected" by PLM. This report relates only to the samples tested and may not be reproduced, except in full, without the written approval of SAI. This report may not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. government. Analytical uncertainty available upon request. Scientific Analytical Institute participates in the NVLAP Proficiency Testing program. Unless otherwise noted blank sample correction was not performed. Estimated MDL is 0.1%.

Lachlan Krenz (12)

Analyst

Approved Signatory



Company Contact Information	
Company: JTL Services LLC	Contact: Jay Leonard
Address: 3999 Sandevosa Road Fayetteville, NC 28312	Phone <input checked="" type="checkbox"/> : 910-237-3519
	Fax <input type="checkbox"/> :
	Email <input checked="" type="checkbox"/> : moldservicesjtl@aol.com

Billing/Invoice Information	Turn Around Times	
Company: Credit Card on File	90 Min. <input type="checkbox"/>	48 Hours <input type="checkbox"/>
Contact: CDF- 0418-96-1283	3 Hours <input type="checkbox"/>	72 Hours <input type="checkbox"/>
Address: 1161 Baysden Ct. Fayetteville NC	6 Hours <input type="checkbox"/>	96 Hours <input type="checkbox"/>
	12 Hours <input checked="" type="checkbox"/>	120 Hours <input type="checkbox"/>
	24 Hours <input type="checkbox"/>	144+ Hours <input type="checkbox"/>

PO Number: \_\_\_\_\_  
 Project Name/Number: \_\_\_\_\_

Asbestos Test Types	
PLM EPA 600/R-93/116 (PLM)	<input checked="" type="checkbox"/>
Positive stop	<input type="checkbox"/>
PLM Point Count 400 (PT4)	<input type="checkbox"/>
PLM Point Count 1000 (PTM)	<input type="checkbox"/>
PCM NIOSH 7400-A Rules (PCM)	<input type="checkbox"/>
B Rules (PCB) <input type="checkbox"/> TWA (PTA) <input type="checkbox"/>	
TEM AHERA (AHE)	<input type="checkbox"/>
TEM Level II (LII)	<input type="checkbox"/>
TEM NIOSH 7402 (TNI)	<input type="checkbox"/>
TEM Bulk Qualitative (TBL)	<input type="checkbox"/>
TEM Bulk Chatfield (TBS)	<input type="checkbox"/>
TEM Bulk Quantitative (TBQ)	<input type="checkbox"/>
TEM Wipe ASTM D6480-05	<input type="checkbox"/>
TEM Microvac ASTM D5755-02	<input type="checkbox"/>
TEM Water EPA 100.2 (TW1)	<input type="checkbox"/>
Other: _____	<input type="checkbox"/>

Sample ID #	Volume/Area	Comments
1		Hallway upstairs ceiling surfacing
2		Bed Room upstairs Rear ceiling surfacing
3		Living Room ceiling surfacing
4		Master Bedroom ceiling surfacing
5		Garage ceiling surfacing
6		Kitchen wall joint compound
7		Hallway wall joint compound
8		upstairs Bathroom joint compound
9		Sheetrock wall
10		Roofing felt paper
11		Roofing shingles
12		Attic Insulation

Accepted   
 Rejected   
 Total # of Samples \_\_\_\_\_

Relinquished by	Date/Time	Received by	Date/Time
		JGL 4-9 10:30 AM	