



Bulk Asbestos Analysis

By Polarized Light Microscopy
EPA Method: 600/R-93/116 and
40 CFR, Part 763, Subpart E, App.E



Customer: JTL Services
3999 Sanderosa Rd.
Fayetteville, NC 28312

Attn: Jay Leonard

Lab Order ID: 10079436

Analysis: PLM

Date Received: 04/09/2025

Date Reported: 04/09/2025

Project: COF- 0429-27-6363 5525 Meharry Drive
Fayetteville NC

Sample ID	Description	Asbestos	Fibrous Components	Non-Fibrous Components	Attributes
Lab Sample ID	Lab Notes				Treatment
1	Joint Compound	None Detected		100% Other	White Non-Fibrous Homogeneous
10079436_0001					Dissolved
2	Sheetrock Rock	None Detected	5% Cellulose	95% Other	Gray Non-Fibrous Homogeneous
10079436_0002					Dissolved
3	Insulation	None Detected	80% Fiber Glass	20% Perlite	White, Yellow Fibrous Homogeneous
10079436_0003					Dissolved
4	Shingles	None Detected	5% Fiber Glass	95% Other	Black Non-Fibrous Homogeneous
10079436_0004					Dissolved

Disclaimer: Due to the nature of the EPA 600 method, asbestos may not be detected in samples containing low levels of asbestos. We strongly recommend that analysis of floor tiles, vermiculite, and/or heterogenous soil samples be conducted by TEM for confirmation of "None Detected" by PLM. This report relates only to the samples tested and may not be reproduced, except in full, without the written approval of SAI. This report may not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. government. Analytical uncertainty available upon request. Scientific Analytical Institute participates in the NVLAP Proficiency Testing program. Unless otherwise noted blank sample correction was not performed. Estimated MDL is 0.1%.

Kiersten Smith (4)

Analyst

Approved Signatory

